

# **ORIGINAL ARTICLE**

King Saud University

# Arabian Journal of Chemistry

www.ksu.edu.sa



www.sciencedirect.com

# Competitive extraction of Cu(II), Zn(II), Ni(II), and Mn(II) cations using acetyl acetone and benzoyl acetone as carriers



# A. Nezhadali \*, A. Sadeghi, M. Roigar

Department of Chemistry, Payame Noor University (PNU), Mashhad, Iran

Received 4 January 2011; accepted 2 February 2011 Available online 2 March 2011

# **KEYWORDS**

Extraction; Benzoyl acetone; Acetyl acetone; pH; Cation

Abstract The competitive metal ion extraction of Cu(II), Ni(II), Zn(II) and Mn(II) with acetyl acetone and benzoyl acetone were examined and compared with each other. The experiments were buffered (acetic acid/sodium acetate and formic acid/sodium formate) at pH 3-7. The extraction behaviors for Cu(II), using both acetyl acetone and benzoyl acetone are similar. In fact the extraction behavior for Cu(II) is much better than the other cations. The extraction results are closely parallel for the other cations using the present ligands. The concentration in extraction experiments for the cations and ligands used was 10 mM and 1.0 mM, respectively.

© 2011 Production and hosting by Elsevier B.V. on behalf of King Saud University.

# 1. Introduction

Solvent extraction has been widely used as a pre-concentration method for analytical applications. Also, conventional solvent extraction involving chelating extractants (or ionophores) dissolved either in organic solvents or in water, is an important industrial technique for the recovery and refining of metals from dilute solutions (Brooks, 1993; Ismael and Tondre, 1994; Benedetto et al., 1995; Matsuyama et al., 1996; Seddon, 1997; Earle and Seddon, 2000). Solvent extraction

E-mail address: aziz\_nezhadali@yahoo.com (A. Nezhadali). Peer review under responsibility of King Saud University.



processes based on simple organic complexing extractants are often used commercially for the recovery and purification of metal ions. Metal ion extraction depends on ligand structure, pH of solution, type of solvent, temperature and time of extraction. The requirement to limit industrial waste in the natural environment is responsible for the increase in the number of research programs devoted to the improvement of technical processes for the separation and recuperation of valuable and/or toxic species (Canet and Seta, 2001). There have now been a considerable number of investigations of the competitive transport and solvent extraction of transition metal cations through bulk liquids using a wide range of synthetic macrocyclic or acyclic derivatives ionophores (Lee et al., 2002; Kim et al., 2000; Fainerman-Melnikova et al., 2004; Nezhadali, 2006, 2010).

The main aim of the present research is to investigate the competitive extraction of Cu(II), Zn(II), Ni(II) and Mn(II) cations. We used acetyl acetone and benzoyl acetone as carrier agent for the competitive metal ion extraction of Cu(II),

<sup>\*</sup> Corresponding author. Tel.: +98 511 8683968; fax: +98 511 8683001.

Ni(II), Zn(II) and Mn(II). The structure of benzoyl acetone and acetyl acetone is shown in I and II, respectively.



# 2. Experimental

#### 2.1. Materials and solutions

All reagents were of analytical grade and used without further purification. All aqueous solutions were prepared with double distilled deionized water. The standard stock solution of Cu(II), Mn(II), Zn(II), and Ni(II) was prepared by dissolving nitrate salts of them. A 1.0 mM stock solution of acetyl acetone and benzoyl acetone was prepared in dichloromethane.

#### 2.2. Instrumental

Concentrations of cations were obtained using a Philips PU9100X atomic absorption spectrometer. The extraction samples were shaken on an IKA-WERKE shaker. All of the pH measurements were carried out by 741 Metrohm pH meter.

#### 2.3. Procedure

The competitive metal ion extraction from an aqueous phase into a dichloromethane phase was employed. The aqueous phase was buffered at pH 3.5–7.0 using sodium acetate/acetic acid and sodium formate/formic acid. The metal ions present were Cu(II), Mn(II), Zn(II) and Ni(II) as their nitrate salts at a concentration of 10 mM. The extractions were carried out in sealed flasks (25 ml). The flasks were shaken for 24 h on a mechanical shaker (at 25 °C). The metal ion concentrations were determined after each extraction experiment, using atomic absorption spectrophotometer. Each experiment was performed in triplicate runs and the reported value is the average of them.

The optimal value for pH was used to optimize ligands concentration. Alternatively, the obtained values were used in the optimizations of time and finally, all these values were used to optimize the rate of shaking on the extraction experiments.

#### 3. Results and discussion

# 3.1. Extraction with benzoyl acetone

To obtain optimum conditions with the ligand, effects of pH, time, rate of shaking and concentration of the ligand was investigated.

#### 3.1.1. pH effect

Most chelating ligands are conjugate bases of weak acid groups and, accordingly, have a very strong affinity for hydrogen ions. The pH, therefore, will be a very important factor in the separation of metal ions by chelating, because it will determine the values of the conditional stability constants of the metal complexes on the surface of the sorbent. The extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) using the ligand in different pH have been done. Data given in Table 1 shows that best pH for extraction is 6.5 and for the other cations, extraction percent is zero.

# 3.1.2. Time effect

The effect of time on the extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) with benzoyl acetone in different times has been done. As shown in Fig. 1 the extraction of Cu(II) from the aqueous feed phase into the organic phase occurs very rapidly and after 1 h is constant. It means after this time extraction% do not have variation.

#### 3.1.3. Effect of shaking rate

The competitive extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) with benzoyl acetone in different rate of shaking has been done. In order to explore the effect of stirring speed, the extraction experiments were performed at five different speeds, 0, 100, 150, 300, 500 and 700 rpm. As shown in Fig. 2 the convenient results are found with 100 rpm. It means, the shaking rate over this amount, does not have any effect on extraction percent. So, this shaking rate was used for the experiments.

## 3.1.4. Effect of the ligand concentration

The extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) with benzoyl acetone in different concentration of



**Figure 1** The effect of extraction time on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, pH 6.5, benzoyl acetone in dichloromethane 5 mM, shaking rate 300 rpm.



Figure 2 The effect of shaking rate on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, pH 6.5, benzoyl acetone in dichloromethane 5 mM and extraction time 1 h.



**Figure 3** The effect of benzoyl acetone concentration on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, pH 6.5, shaking, rate, 100 rpm and extraction time 1 h.

ligand has been done. For this purpose concentration of ligand from 0.1 to 10 mM was studied. As shown in Fig. 3, there is a linear relation between the ligand concentration and extraction percent of Cu(II) in the competitive extraction experiments. On the other hand, the more amounts of ligand may affect on the selectivity of it. So, the 10 mM of the ligand was used for the experiments.

## 3.2. Extraction with acetyl acetone

To obtain optimum condition with this ligand, effects of pH, time, rate of shaking and concentration of ligand were investigated.

#### 3.2.1. pH effect

The extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) with acetyl acetone in different pH has been done. Data given in Table 2 shows that best pH for extraction is 6.0 and for other cations, concentration percent is zero. As shown in Table 2, the ligand is completely selective in pH 6–7 for Cu(II). At lower pH values, there is a decrease in the percentage transport of copper, due to the diminished complexing

**Table 1** The effect of pH on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, benzoyl acetone in dichloromethane 1 mM, shaking, rate 300 rpm and extraction time 1 h.

pH of aqueous phase	% Extraction				
	Cu(II)	Zn(II)	Mn(II)	Ni(II)	
3.0	0	0	0	0	
3.5	0	0	0	0	
4.0	5.8	0	0	0	
4.5	5.9	0	0	0	
5.0	12.6	0	0	0	
5.5	12.9	0	0	0	
6.0	13.2	0	0	0	
6.5	25.1	0	0	0	
7.0	22.1	0	0	0	

**Table 2** The effect of pH on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, acetyl acetone in dichloromethane 1 mM, shaking, rate 300 rpm and extraction time 1 h.

pH of aqueous phase	% Extraction				
	Cu(II)	Zn(II)	Mn(II)	Ni(II)	
3.0	0	0	0	0	
3.5	0	0	0	0	
4.0	0	0	0	0	
4.5	5.6	0	0	0	
5.0	8.9	0	0	0	
5.5	13.4	0	0	0	
6.0	18.9	0	0	0	
6.5	18.6	0	0	0	
7.0	18.5	0	0	0	

ability of the ligand at such pH values. The Irving-Williams series of stability of metal complexes with dipositive metal ions increases in the series Ba-Cu, decreases with Zn (Huheey, 1983). The trend is essentially independent of the ligand. The position of Cu(II) is considered out-of-line with predictions based on Crystal Field Theory and is probably a consequence of the fact that Cu(II) often forms distorted octahedral complexes.



**Figure 4** The effect of extraction time on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, pH 6, acetyl acetone in dichloromethane 5 mM, shaking rate: 300 rpm.



Figure 5 The effect of shaking rate on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, pH 6, acetyl acetone in dichloromethane 5 mM and extraction time 1 h.



**Figure 6** The effect of benzoyl acetone concentration on the competitive extraction of Cu(II). Conditions: Initial concentration of [Cu(II), Mn(II), Zn(II) and Ni(II)] 10 mM, pH 6, shaking, rate, 100 rpm and extraction time 1 h.

## 3.2.2. Extraction time effect

The competitive metal ion extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) using acetyl acetone as the ligand in different times has been done. As shown in Fig. 4 extraction around 1 h made complete and after this time extraction % do not have variation.

#### 3.2.3. Rate of shaking

The extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) with acetyl acetone in different rate of shaking has been done. As shown in Fig. 5 the optimum condition is found with 100 rpm and the rate of shaking over this, does not has any effect on extraction percent.

#### 3.2.4. The ligand concentration effect

Competitive extraction experiments of Cu(II), Mn(II), Zn(II), and Ni(II) with acetyl acetone in different concentration of ligand has been done. For this purpose concentration of ligand from 0.1 to 10 mM was investigated. The results are shown in Fig. 6. As it was expected the maximum amount of extraction is given in concentration of 1.0 mM of ligand.

# 4. Conclusion

The results show both benzoyl acetone and acetyl acetone are good ligands for selective extraction of Cu(II) from aqueous nitrate solution in the presence of Zn(II), Ni(II) and Mn(II) cations. The efficiency of the extractions depends on the conditions of competitive extraction experiments. It was found the optimal values of pH, extraction time, shaking rate and the ligand concentrations for the both ligands are nearly the same.

#### References

- Benedetto, J.D.S., Soares, M.L., Grewal, I., Dreisinger, D.B., 1995. Recovery of raremetals with a new organophosphorus extractant. Sep. Sci. Technol. 30, 3339.
- Brooks, C.S., 1993. Partitioning in aqueous to-phase systems. A comprehensive bibliography in three parts. Sep. Sci. Technol. 28, 579.
- Canet, L., Seta, P., 2001. Extraction and separation of metal cations in solution by supported liquid membrane using lasalocid A as carrier, L. Pure Appl. Chem. 73, 2039.
- Earle, M.J., Seddon, K.R., 2000. Green solvents for the future. Pure Appl. Chem. 72, 1391.
- Fainerman-Melnikova, M., Nezhadali, A., Rounaghi, Gh., McMurtrie, J.C., Kim, J., Gloe, 2004. The interaction of selected transition and post-transition metal ions with a mono-N-benzylated  $O_2N_3$ -donor macrocycle and its xylyl-bridged ring analogue. J. Chem. Soc. Dalton Trans. 1, 22.
- Huheey, J.E., 1983. Inorganic Chemistry. Harper and Row publishers, New York, p. 317.
- Ismael, M., Tondre, C., 1994. Extraction equilibrium of copper from ammoniacal media with Lix 54. Sep. Sci. Technol. 29, 651.
- Kim, J., Leong, A., Lindoy, L.F., Nachbaur, J., Nezhadali, A., Rounaghi, Gh., Wei, G., 2000. Metal-ion recognition competitive bulk membrane transport of transition and post transition metal ions using oxygen-nitrogen donor macrocycles as ionophores. J. Chem. Soc., Dalton Trans., 3453
- Lee, S.S., Yoon, I.I., Park, K.-M., Jung, J.H., Lindoy, L.F., Nezhadali, A., Rounaghi, Gh., 2002. Competitive bulk membrane transport and solvent extraction of transition and post transition metal ions using mixed-donor acyclic ligands as ionophores. J. Chem. Soc., Dalton Trans., 2180
- Matsuyama, H., Miyamoto, Y., Teramoto, M., Goto, M., Nakashio, F., 1996. Adsorption of metal cations by hydrous aluminium(III) or iron(III) hydroxide precipitates: enhancement by EDTA and related chelate molecules. Sep. Sci. Technol. 31, 799.
- Nezhadali, A., 2006. Selective transport of copper(II) ion across a polymer membrane incorporating a difunctional schiff-base iono-phore. J. Incl. Phen. 54, 307.
- Nezhadali, A., 2010. Selective transport of Ag (I) ion across a bulk liquid and polymer membranes incorporated with di-N-benzylated O3N2 donor. Macrocycles Chni. Chem. Lett. 21, 1111.
- Seddon, K.R., 1997. The influence of chloride, water and organic solvents on the physical properties of ionic liquids. J. Chem. Technol. Biotechnol. 68, 351.